



BESLER
GLASS FIBER

PT

Direct Roving For
Pultrusion

PRODUCT FEATURES

- Boron-free ECR-glass
- Environment friendly
- Good unwinding
- Low fuzz
- Good & fast wettability
- Good surface finish
- High strand integrity

PRODUCT SPECIFICATION

PT

• Glass Type	ECR (B-Free)				
• Filament Diameter (μ)	16	17	17	24	
• Roving Tex (g/10 ³ m)	600	1200	2400	4800±	% 7
• Moisture Content (%)	Max. 0,1				
• Sizing Type	Silane				
• Loss of Ignition (%)	0,55±0,15				
• Compatability	Epoxy, polyester, vinylester resins				

PACKAGING

Type	Pallet Dimensions (cm)	Bobbins per Pallet	Layers per Pallet	Pallet Height (cm)	Product Net Weight per Pallet
Bulk Packaging	93 x 123	48	4	120	840

BOBIN DIMENSION

Weight (kg)	Inner diameter (mm)	Outer Diameter(mm)	Height(mm)
Nom. 17,5	160	295	255

STORAGE

Products should be stored in original package in dry and dust free area.
Storage temperature is between 10°C - 30°C at humidity between 50% - 75%. Pallets must be single stacked.

WARRANTY

All physical & chemical properties represent average values and subject to normal production variations.
The specifications are also subject to change. For current information please contact Beşler Office.



BEŞLER TEKSTİL SANAYİ ve TİC. A.Ş.

Address: Sultansazı Mh. 10. Cd. No:1 O.S.B. İncesu / Kayseri / TÜRKİYE M: +90 (535) 545 18 93 T: +90 (352) 504 06 02 (pbx)

www.beslerglassfiber.com.tr